

AWF METAL COAT H.T.C.

AWF Metal Coat H.T.C. is a single pack product based on polymers and heat resistant pigments providing heat resistance up to 500°C but will resist higher temperatures for short periods.



All surfaces should be clean, dry and free from grease, oil, rust and flaking paint work. Surfaces should be shot blasted to give the best results alternatively, wire brushing is recommended making sure to remove as much scale as possible.



AWF Metal Coat H.T.C. is a single pack component

Stir well before use.



Drying, Curing times at 20°C

Touch dry: 30 mins

Hard dry: 1 – 2 hours

Full cure: 24 hours

Overcoating: Before 30 mins or after 24 hours

Do not abrade between coats.



N/A Single pack component

APPLICATION DETAILS.



Airless Spray : Ready to use

Brushing: Ready to use
All equipment must be cleaned immediately after use with AWF Universal Cleaner.



Theoretical coverage rate
8m² per litre at 40 microns dry film thickness



N/A



Use within 12 months of purchase

Store in original sealed containers



As long as good practice is observed, AWF Metal Coat H.T.C. can be safely used.

Maintain adequate ventilation

A fully detailed Material Safety Data Sheet is available on request.

If you have any questions or queries regarding this data sheet or the application of this product, please contact us before you use the product.